

TECHNICAL SHEET

Ag38MnNi

Product name

Ag38MnNi

Class of product

Silver based brazing alloy, cadmium-free

Corresponding standards (external brazing layers)

ISO 17672 -----
EN 1044 -----
AWS A5.8-04 -----
DIN 8513 -----

Nominal composition of external brazing layers (weight %)

Ag: 38
Cu: 26
Zn: 24
Ni: 4,5
Mn: 7,5

Physical and technical properties

Melting range (Solidus – Liquidus): 650 – 690 °C
Brazing temperature: ~ 700 °C
Density: 8,9 g/cm³
Recommended joint gap: 0,1 – 0,25 mm
Continuous service joint operating temp.: -200 / +200 °C

Range of application

Ag38MnNi is a special application, cadmium-free, silver brazing alloy, with very good flow properties.

It can be used to braze a wide variety of different metals and alloys, and is particularly suited to join difficult to braze materials such as cemented carbides, hard-metal, tungsten carbides, etc.

The addition of Nickel and Manganese improves the wetting properties and the corrosion resistance of the alloy, and the tensile strength of brazed joints.

Brazing procedures range from flame to induction techniques.

When brazing in an oxidizing environment a proper flux should be used.

Tensile strength of joints brazed with Ag38MnNi will generally exceed base metals strength. Joint strength is however a function of various factors, such as: type of base metals to be joined, type of joint, joint clearance, brazing procedure, etc.

Typical applications are in the carbide and diamond tipped tools industry.

Characteristics Make-up

| | | |
|-------------------|-----------------------|------------------------|
| Rods: | Ø 0,5 ⇒ 4,0 mm | Length: 500 / 1.000 mm |
| Flux Coated Rods: | Ø 1,5 ⇒ 3,0 mm | |
| Wires: | Ø 0,25 ⇒ 3,0 mm | Spoiled and coiled |
| Strips: | Thickness: 0,1 ⇒ 1 mm | Width: 1,3 ⇒ 80 mm |

Rings

Preforms from Wire and from Strip

Pastes & Powders

Other dimensions are available upon request.

NOTE:

Information contained in this data sheet are based on the knowledge available to us at the date of last document revision and are believed to be accurate. Anyway, no data contained in this data sheet may be regarded as an assurance of any property of the product. We do not assume any responsibility for results obtained or damages occurred from the use of the information contained in this data sheet. We do not assume any responsibility for any un-proper use of the product. Users should verify the suitability and completeness of information with regard to specific use the product. As end use of product is not under our direct control, it is the user's responsibility to fully comply with applicable laws and regulations in safety and hygiene.

STELLA s.r.l.

Via Marconi 26 – 21041 ALBIZZATE (VA) – ITALY

Tel. +39-0331-985787 – Fax +39-0331-985803

info@stella-welding.com - www.stella-welding.com